

## Technical Information

**ARTICLE** EL 74/8  
**APPLICATION** PLASTICIZED EXTRUSION



Characteristics	Method	Unit	Tolerance	Value
Density	ISO 1183/1	g/cm <sup>3</sup>	(±0,02)	1,41
Shore A Hardness	ISO 868	SH.A	(±3)	73
Tensile strenght	ISO 527	MPa	>=	12,7
Elongation at Break	ISO 527	%	>=	300
Cold Flex	ISO 458	°C	(±5)	-33
Thermal Stability 200°C	EN 60811-3-2	min	>=	100

**NOTE :** MIGRATION ON PS FOIL 14 gg x 70°C (ISO 177) < 50 mg

*The technical information reported above comes from laboratory analysis; it should be considered indicative and not as a binding agreement. For any further information please contact our technical service.*

20/10/2021

Page 1 of 1